


PRODUCT DATA SHEET

Non-Functionalized Surfactant Stabilized Gold Nanoparticles



Citrate Capped

Catalog Numbers: CG-5-XX, CG-10-XX, CG-15-XX, CG-20-XX, CG-30-XX, CG-40-XX, CG-50-XX, CG-60-XX, CG-70-XX, CG-80-XX, CG-90-XX, CG-100-XX, CG-150-XX, CG-200-XX, CG-250-XX, CG-300-XX, CG-400-XX

Description

Cytodiagnostics Non-Functionalized Surfactant Stabilized Gold Nanoparticles have been optimized for modification of the gold surface with thiolated ligands such as oligonucleotides and polyethylene glycols. These nanoparticles are also ideal for use in applications requiring harsher conditions (i.e. higher salt concentrations) than can be tolerated by standard gold nanoparticles.

Our gold nanoparticles are available in 17 different sizes ranging from 5-400nm, are more than 95% spherical and have uniform size distribution (CV <12%).

For custom sizes, formulations or bulk quantities please contact our customer service department.

Features

- Superior size distribution compared to the leading competitor; available from 5nm to 400nm.
- Higher salt stability (30mM NaCl, 30 minutes) compared to standard gold nanoparticles.
- Gold surface accessible for further functionalization
- Also available with multiple surface functionalities to suit all your needs. (Please see Cytodiagnostics PEGylated and Functionalized Gold Nanoparticles).

Applications

Ideal for development of oligonucleotide gold conjugates for use in immunoblotting, lateral flow assays, biological sensor development and others.

Characteristics




Core diameter: 5-400nm (Coefficient of Variance < 12%)

Polydispersity Index (PDI): < 0.20

Concentration: OD=1 (~ 0.05 mg/ml)

Absorbance (λ_{max}): 510-570nm

Supplied in 0.1mg/ml citrate buffer supplemented with a proprietary stabilizing solution.



Diameter (nm)	Peak SPR Wavelength (nm)	NPS/ml	Wt. Conc. (mg/ml)	Molar Ext ($M^{-1}cm^{-1}$)	Size Dispersity (+/-nm)	Particle Volume (nm^3)	Surface Area (nm^2)	Surface/Volume Ratio	Particle Mass (g)	Molar Mass (g/mol)	Molar Conc.
5	515-520	5.47E+13	6.94E-02	1.10E+07	<15%	6.54E+01	7.85E+01	1.2	1.27E-18	7.64E+05	9.08E-08
10	515-520	5.98E+12	6.07E-02	1.01E+08	<15%	5.24E+02	3.14E+02	0.6	1.02E-17	6.11E+06	9.93E-09
15	520	1.64E+12	5.61E-02	3.67E+08	<12%	1.77E+03	7.07E+02	0.4	3.43E-17	2.06E+07	2.72E-09
20	524	6.54E+11	5.31E-02	9.21E+08	<12%	4.19E+03	1.26E+03	0.3	8.12E-17	4.89E+07	1.09E-09
30	526	1.79E+11	4.91E-02	3.36E+09	<12%	1.41E+04	2.83E+03	0.2	2.74E-16	1.65E+08	2.98E-10
40	530	7.15E+10	4.65E-02	8.42E+09	<12%	3.35E+04	5.03E+03	0.15	6.50E-16	3.91E+08	1.19E-10
50	535	3.51E+10	4.45E-02	1.72E+10	<10%	6.54E+04	7.85E+03	0.12	1.27E-15	7.64E+08	5.83E-11
60	540	1.96E+10	4.30E-02	3.07E+10	<10%	1.13E+05	1.13E+04	0.1	2.19E-15	1.32E+09	3.25E-11
70	548	1.20E+10	4.17E-02	5.03E+10	<10%	1.80E+05	1.54E+04	0.086	3.48E-15	2.10E+09	1.99E-11
80	553	7.82E+09	4.06E-02	7.70E+10	<10%	2.68E+05	2.01E+04	0.075	5.20E-15	3.13E+09	1.30E-11
90	564	5.37E+09	3.97E-02	1.12E+11	<8%	3.82E+05	2.54E+04	0.067	7.40E-15	4.46E+09	8.92E-12
100	572	3.84E+09	3.89E-02	1.57E+11	<8%	5.24E+05	3.14E+04	0.06	1.02E-14	6.11E+09	6.37E-12
150		3.60E+09	1.20E-01		<8%	1.77E+06	7.07E+04	0.04	3.43E-14	2.06E+10	5.98E-12
200		1.91E+09	1.55E-01		<8%	4.19E+06	1.26E+05	0.03	8.12E-14	4.89E+10	3.17E-12
250		7.08E+08	1.13E-01		<8%	8.18E+06	1.96E+05	0.024	1.59E-13	9.55E+10	1.18E-12
300		4.50E+08	1.24E-01		<8%	1.41E+07	2.83E+05	0.02	2.74E-13	1.65E+11	7.48E-13
400		1.88E+08	1.22E-01		<8%	3.35E+07	5.03E+05	0.015	6.50E-13	3.91E+11	3.12E-13

Storage

This product should be stored at 4°C. **DO NOT FREEZE.** If stored unopened and as specified, Cytodiagnostics gold nanoparticles are stable for at least 6 months.

Handling

When stored for a long period of time gold nanoparticles may sediment at the bottom of the flask, which is especially true for larger particle sizes. Prior to use, re-suspend the sedimented particles by swirling until a homogenous solution is obtained.

To maintain optimal performance, and stability of the colloidal gold, care should be taken to use clean storage containers if using other than supplied with the product.

Washing of Gold Nanoparticles

Although it is not generally necessary to wash the gold nanoparticles prior to use, some applications may require additional washing procedures. The easiest way to remove possible contaminants in the nanoparticles solution is by

centrifugation. Centrifugation force is dependent on size of the gold nanoparticles and should be adjusted according to Table I for optimal performance.

Note I: Since non-functionalized gold nanoparticles are sensitive to salt containing buffers, re-suspension should always be performed in ultra-pure water to prevent irreversible aggregation. Irreversible aggregation is characterized by a clear to bluish solution upon the addition of salt.

Note II: Please note that centrifugation can induce aggregation. To prevent aggregation it may be necessary to add Tween 20 at a concentration of 0.025% w/v.

Procedure

1. Place 1ml aliquot of colloidal gold in a 1.5ml micro centrifuge tube
2. Centrifuge the gold nanoparticles for 30 minutes using the appropriate G force determined by referencing Table I.
3. Remove the supernatant and re-suspend in an appropriate volume of ultra-pure water.
4. Vortex to re-disperse the particles.

Table I. Appropriate G forces for centrifugation of gold nanoparticles. Note that recommended conditions are for a volume of 1ml and centrifugation using a microcentrifuge, except for 5nm gold nanoparticles that requires an ultracentrifuge.

Size (nm)	Speed (g)	Time (min)
5	100,000	30
10	17,000	60 (~50% recovery)
15	17,000	30
20	6,500	30
30	4,500	30
40	2,500	30
50	2,000	30
60	1,125	30
80	600	30
100	400	30
150	180	30
200	100	30

Protein Conjugation

A recommended starting protocol for conjugation of proteins to Cytodiagnostics gold nanoparticles can be found online at in the Technical Reference Section.

NOTE: For optimized high efficiency peptide, protein, or antibody absorption, consider using Cytodiagnostics Non-Functionalized Standard or Reactant Free Gold Nanoparticles.

Product Safety and Handling

This product is for R&D use only, not for drug, household, or other uses. Please review the material safety datasheet (MSDS) available online for proper safety and handling procedures.

Ordering Information

For ordering call 866-344-3954 or visit us online.

Canada, Europe, Asia, Pacific and Africa

919 Fraser Drive, Unit 11, Burlington, ON Canada L7L 4X8
Tel: 866-344-3954 Fax: 289-204-9100
www.cytodiagnostics.com

United States, Mexico, South and Central America

5867 South Garnett Road, Tulsa, Oklahoma 74146 USA
Tel: 866-344-3954 Fax: 289-204-9100
www.cytodiagnostics-us.com

Catalog Number	Description	Sizes
CG-5-XX*-YY**	5nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-10-XX*-YY**	10nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-15-XX*-YY**	15nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-20-XX*-YY**	20nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-30-XX*-YY**	30nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-40-XX*-YY**	40nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-50-XX*-YY**	50nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-60-XX*-YY**	60nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-70-XX*-YY**	70nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-80-XX*-YY**	80nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-90-XX*-YY**	90nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-100-XX*-YY**	100nm Stabilized Gold Nanoparticles	20ml, 100ml, 500ml or 1000ml
CG-150-XX*-YY**	150nm Stabilized Gold Nanoparticles	20ml, 100ml, or 500ml
CG-200-XX*-YY**	200nm Stabilized Gold Nanoparticles	20ml, 100ml, or 500ml
CG-250-XX*-YY**	250nm Stabilized Gold Nanoparticles	20ml, 100ml, or 500ml
CG-300-XX*-YY**	300nm Stabilized Gold Nanoparticles	20ml, 100ml, or 500ml
CG-400-XX*-YY**	400nm Stabilized Gold Nanoparticles	20ml, 100ml, or 500ml

*Indicates quantity, e.g. CG-5-20 for 20ml of 5nm Stabilized Gold Nanoparticles

** Indicates Optical Density (OD), either 1 OD, or -10 for 10 OD.

For custom sizes (up to 400nm available), bulk quantities, and custom gold nanoparticle surface chemistry, please contact our customer service department.

Canada, Europe, Asia, Pacific and Africa

919 Fraser Drive, Unit 11, Burlington, ON Canada L7L 4X8
 Tel: 866-344-3954 Fax: 289-204-9100
www.cytodiagnosics.com

United States, Mexico, South and Central America

5867 South Garnett Road, Tulsa, Oklahoma 74146 USA
 Tel: 866-344-3954 Fax: 289-204-9100
www.cytodiagnosics-us.com